

Condi ApS  
Att.: Erik Elmelund Petersen  
Roskildevej 30  
2620 Albertslund

15.09.2022

## Leverandørerklæring

- Vedr. PEHD500 Natur

Vores ordre 10640 jeres ordrenr. Ref.: 21568

Undertegnede Jens Vest-Andersen, Brønnum Plastsnedkeri A/S, erklærer hermed at PEHD500 og - er fremstillet i polyethylen natur af mærket "Röchling", der er produceret af Röchling Group.

Med venlig hilsen



Jens Vest-Andersen

## Technical Data Sheet

### Polystone<sup>®</sup> D natural

#### Product characteristics

- Good mechanical properties
- Very wear-, cutting and scratch resistant
- Physiologically safe

#### Product applications

- Environment and disposal technology
- Cutting boards
- Sports and leisure industry

	Test method	Unit	Guideline Value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g / cm <sup>3</sup>	>0,95
Water absorption	DIN EN ISO 62	%	<0,01
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	>27
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	>1200
Shore hardness	DIN EN ISO 868	scale D	65
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	130 ... 135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,40
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> / K	150 ... 230
Service temperature, long term	Average	°C	-100 ... 80
Service temperature, short term (max.)	Average	°C	80
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	79
<b>Electrical properties</b>			
Dielectric constant	IEC 60250		2,3
Dielectric dissipation factor (10 <sup>6</sup> Hz)	IEC 60250		0,0002
Volume resistivity	DIN EN 62631-3-1	Ω * cm	>10 <sup>14</sup>
Surface resistivity	DIN EN 62631-3-2	Ω	>10 <sup>14</sup>
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV / mm	>40

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.