

**PROBARRIER Greaseproof Paper**

wet strength  
 machine finish  
 natural white  
 Kit 4-6

Property		Unit	Norm	Typical value
<b>Substance</b>		gsm	ISO 536	45
<b>Caliper</b>		µm	ISO 534	57
<b>Moisture</b>		%	ISO 287	6
<b>Smoothness, Bekk</b>	TS	sec	ISO 5627	25
<b>Smoothness, Bekk</b>	WS	sec	ISO 5627	25
<b>Tensile strength</b>	MD	N/15mm	ISO 1924-2	80
<b>Tensile strength</b>	CD	N/15mm	ISO 1924-2	40
<b>Wet tensile strength</b>	MD	N/15mm	ISO 3781	8
<b>Wet tensile strength</b>	CD	N/15mm	ISO 3781	4
<b>Water-absorption Cobb60</b>	TS	gsm	ISO 535	20
<b>Water-absorption Cobb60</b>	WS	gsm	ISO 535	20
<b>Reflectance -R 457-</b>	TS	%	ISO 2470 / D65	87
<b>Determination of grease resistance</b>	TS		ISO 16532-2	5
<b>Determination of grease resistance</b>	WS		ISO 16532-2	5

free of optical brighteners

the paper grade is in compliance with :

- Regulation (EC) No. 1935/2004
- German Food Law LFGB §30 and 31
- German Recommendation XXXVI of the Federal Institute for Risk Assessment

These are target values and may change without prior notice.

22.05.2023 S&Q/FRIHEN